

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
5 April 2001 (05.04.2001)

PCT

(10) International Publication Number
WO 01/23316 A1

- (51) International Patent Classification⁷: C03C 13/00 (74) Agent: SUTTO, Luca; Bugnion S.p.A., Viale Lancetti, 17, I-20158 Milano (IT).
- (21) International Application Number: PCT/IT00/00380
- (22) International Filing Date:
27 September 2000 (27.09.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
MI99A002040 30 September 1999 (30.09.1999) IT
- (71) Applicants (for all designated States except US):
TECHINT COMPAGNIA TECNICA INTERNAZIONALE S.P.A. [IT/IT]; Via Monterosa, 93, I-20149 Milan (IT). POLIGLAS S.A. [ES/ES]; Ctra. de Barcelona Km., 66, Barbera del Valles, Barcelona (ES).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): LA GRECA, Marco [IT/IT]; Via Vittorio Veneto, 9/4, I-20068 Peschiera Borromeo (IT). MASSINI, Roberto [IT/IT]; Via Marchesi, 11, I-24043 Caravaggio (IT). PASALAIGUA HUGUET, Jorge [ES/ES]; Calle Ignasi Sarro', 1, E-43800 Valls Tarragona (ES).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:
- With international search report.
 - Before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments.
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: A GLASS FIBER COMPOSITION

(57) Abstract: The invention relates to a biologically-degradable glass fiber composition having good mechanical properties, good workability and in particular fiber-forming-capability features and resistance to humidity. The concentrations expressed in percent by weight for each component being the object of the invention are: SiO₂: 61 to 66; Al₂O₃: 1.1 to 2.1; (CaO+MgO): higher than 9; (Na₂O+K₂O): higher than 18; B₂O₃: 4 to 15; P₂O₅: 0 to 5; SO₃: 0 to 1; Fe₂O₃: 0 to 0.5; Others: less than 2.

WO 01/23316 A1

A GLASS FIBER COMPOSITIONDescription

5 The present invention relates to a glass fiber composition. In particular, the present invention relates to a biologically-degradable or bio-soluble glass fiber composition, adapted for production of panels and felts of glass wool. These goods are commonly used in the civil
10 and industrial field in the form of heat insulators and/or sound-proofing materials.

Presently known are many glass fiber compositions showing some biological degradability or bio-solubility
15 (solubility of a glass fiber in contact with a biological liquid). It is in fact to be recognized that the biological degradability in glass fibers was in the past and has been till now the object of many studies because a relation seems to exist between this biological
20 degradability and the cancerogenous properties that the glass fiber may show if it is introduced into or absorbed by a human or animal body.

In particular, it has been recently ascertained that a
25 higher bio-solubility can reduce the cancerogenous effects of the glass fibers increasing the capability of the human or animal body to get rid of the possibly-absorbed fibers.

30 In addition to bio-solubility, the glass fiber compositions of industrial concern must at all events also have an appropriate behaviour with reference to properties of physical, chemical and mechanical nature, such as for example: mechanical strength, elasticity,
35 resistance to thermal fronts and chemical and atmospheric agents, workability, flexibility, fineness,

length/diameter ratio. Also to be taken into account is the economic aspect: it is apparent that too expensive glass fibers cannot be put on the market so as to be competitive.

5

Therefore, greatly felt is a need for a glass fiber composition having a good biological degradability combined with good features with reference to the above mentioned chemical, physical and mechanical properties.

10 In particular, obtaining an economically convenient glass fiber composition having a good biological degradability and at the same time a good resistance to water and humidity is very complicated because the last-mentioned requirement can be hardly reconciled with fibers having
15 a good tendency to dissolve in biological media.

More generally, that which is complicated is coordinating the economical requirements of an industrial production with bio-solubility and with the strength requirements
20 that a fiber must have in order to be able to fulfill the present uses.

It is therefore an aim of the present invention to provide a glass fiber composition which is sufficiently
25 bio-soluble and has a good resistance if brought into contact with water and/or humidity, a good workability, by use of centrifugal techniques for example, a capability of achieving a good heat/soundproof insulation, a good elasticity and reduced brittleness.

30

It is a further aim of the present invention to provide a glass fiber composition having reduced production costs.

35 In an attempt to reach the above-mentioned aims, compositions were proposed in the past in which the SiO_2

and Al_2O_3 content was greatly reduced while corresponding important increases in CaO , MgO , Na_2O , K_2O and B_2O_3 content were carried out thereby obtaining fibers that were weakly efficient in terms of structure, production
5 and costs.

Surprisingly, as better specified during the following detailed description, the Applicants have developed a biologically degradable glass fiber composition in which,
10 by virtue of a particular combination of alkaline and non-alkaline oxides, the SiO_2 and Al_2O_3 content have been greatly reduced, while satisfactory results in terms of bio-solubility have been at the same time achieved.

15 In particular, it is an object of the present invention to provide a biologically degradable or bio-soluble glass fiber composition characterized in that it comprises the following components the counter-actions of which are expressed in percent by weight:

- 20 - SiO_2 : 61 to 66;
- Al_2O_3 : 1.1 to 2.1;
- $(\text{CaO}+\text{MgO})$: higher than 9;
- $(\text{Na}_2\text{O}+\text{K}_2\text{O})$: higher than 18;
- B_2O_3 : 4 to 15;
25 - P_2O_5 : 0 to 5;
- SO_3 : 0 to 1;
- Fe_2O_3 : 0 to 0.5;
- Others: less than 2.

30 The particular combination and concentration of organic oxides gives the glass fiber composition being the object of the present invention good mechanical features, workability, resistance to humidity and excellent heat/soundproof insulation features.

35

Now, the detailed description of some preferential

embodiments of the composition in accordance with the invention will be given and the different components of the glass fiber composition of the invention will be analysed hereinafter; each component will be analysed in order to highlight its behaviour and technical effect in coordination with the other elements in the composition.

Silica (SiO_2) is one of the vitrifying agents present in the composition and helps in forming the glass lattice. Silica gives structural properties to glass. In the concerned composition silica is present in a percent by weight included between 61 and 66.

Alumina (Al_2O_3) was measured very carefully because a too great percentage by weight would act, among other things, in a manner involving decrease in the biological degradability of the resulting glass. At the same time alumina cannot be completely eliminated because a too water-soluble glass would be obtained. A glass without alumina, once reduced to fiber, would not stand too long in contact with humidity. In addition glass, in order to be able to be formed into fibers, must keep its viscosity value within a well-precise range under which it is practically impossible to obtain fibers in an industrial manner. For the above reasons alumina is present in a concentration by weight included between 1.1 and 2.1. Preferably, alumina is present in a concentration by weight included between 1.1 and 1.8.

Calcium oxide (CaO) and magnesium oxide (MgO) stabilize the glass lattice and give the glass structural features. In addition, calcium oxide and magnesium oxide both reduce the glass viscosity and capability of being formed into fibers. More specifically, it should be pointed out that calcium oxide and magnesium oxide contribute to viscosity in a manner different from each

other: magnesium oxide reduces viscosity less than calcium oxide. Calcium oxide and magnesium oxide also affect the biological degradability of the glass fibers.

- 5 In accordance with the invention, use of the combination of the two oxides ($\text{CaO}+\text{MgO}$) in a percent by weight higher than 9 appeared to be advantageous. In particular a MgO content higher than or equal to 2.5 percent by weight appeared to be useful, the calcium oxide oscillations
10 being included in a range between 6.5 and 8 percent by weight.

Sodium oxide (Na_2O) and potassium oxide (K_2O) affect the glass degradability making it higher. At the same time,
15 sodium oxide and potassium oxide also increase the water-solubility of glass. In both cases, the potassium oxide contribution is lower than the sodium oxide contribution. The two alkaline oxides also act on the glass viscosity and therefore the glass capability of being formed into
20 fibers. As already mentioned, viscosity is a parameter of the greatest importance as regards glass workability and formation into fibers. In addition, the two alkaline oxides also somewhat affect the glass brittleness. A compromise between economical factors, industrial
25 workability, brittleness, biological degradability and resistance to water was obtained by combining the two alkaline oxides ($\text{Na}_2\text{O}+\text{K}_2\text{O}$) in a percentage by weight higher than 18. Preferably and originally, the combination of the two alkaline oxides ($\text{Na}_2\text{O}+\text{K}_2\text{O}$) in
30 percent by weight is higher than or equal to 18.50 and lower than or equal to 23. In particular, Na_2O is present in a concentration by weight included between 17.70 and 18.50. In turn, potassium oxide is present in a concentration by weight included between zero and 2 and
35 more preferably it is present in a concentration by weight included between 0.50 and 1.50. It should be noted

that an increase in the concentration by weight of Al_2O_3 follows an increase in the concentration by weight of Na_2O because the glass viscosity, notwithstanding the possible presence of K_2O , becomes too low and therefore
5 an industrially unworkable glass would result.

Boron oxide (B_2O_3) advantageously contributes to the glass fiber elasticity. In particular, a felt of fibers having a good elasticity must be able to be compressed and, once
10 released, to take its original thickness again. Elasticity also helps in ensuring a good workability to the glass, above all during the operations for forming it into fibers. An elastic glass fiber surely is subject to less fractures. Since the alumina content was lowered
15 under 2% by weight and at the same time the Na_2O and K_2O content was increased in order to ensure a good bio-solubility, a weight amount of B_2O_3 at least included between 4 and 15 and preferably between 5 and 15 was originally inserted in order to avoid too brittle a fiber
20 being obtained. At all events boron oxide B_2O_3 also helps in reducing viscosity and has some repercussions from an economical point of view. In addition, boron oxide affects the biological degradability of glass fibers. For the reasons briefly discussed above, when an increase in
25 brittleness occurs, due to an increase in the alkali ($\text{Na}_2\text{O} + \text{K}_2\text{O}$) amount for example, the boron oxide component is increased in the composition but only to such an extent that the manufacturing cost of the glass is not increased too much. For instance (see the above-reproduced Example 1), if sodium oxide is present in a
30 high concentration by weight and aluminium oxide is present in a low concentration, the resulting fiber could be more brittle. In order to compensate for the resulting fiber brittleness, preferably a higher concentration by
35 weight of boron oxide is employed.

Phosphoric anhydride (P_2O_5) is a vitrifying agent and helps in forming the glass lattice. The phosphoric oxide increases the biological degradability and solubility of glass. It increases the biological degradability and
5 solubility of glass to a greater extent than boron oxide.

The phosphoric oxide is present in a percentage by weight included between zero and 5.

- 10 In some cases use of boron oxide in combination with phosphoric oxide P_2O_5 so that the $B_2O_3 + P_2O_5$ concentration by weight would be greater than 5 appeared to be very advantageous. This combination aims at integrating possible losses in the structural and biological-
15 degradability features. In accordance with the invention, should phosphoric oxide be present in a concentration by weight included between zero and less than 0.1, boron oxide is present in a weight amount greater than 5, preferably in a weight amount greater than 5.5. Should
20 phosphoric oxide be present in a concentration by weight included between 0.75 and 1.5, boron oxide is present in an amount by weight lower than 5, preferably lower than 4.5.
- 25 It should be also noted that P_2O_5 can be dangerous for furnaces intended for glass melting so that advisably a percentage by weight of P_2O_5 higher than 1 should never be exceeded.
- 30 Sulfur trioxide (SO_3) proved to affect the composition behaviour by improving the biological degradability of glass without substantially varying its resistance to H_2O . Sulfur trioxide was therefore provided in a percentage by weight included between zero and 1.
35 Preferably sulfur trioxide is present in a percentage by weight included between 0.10 and 0.5.

Ferric oxide (Fe_2O_3) acts on the biological degradability of glass fibers by decreasing it. Therefore it is useful for the ferric oxide to be present in a percentage by weight included between zero and a value not exceeding 5 0.5. Preferably, the ferric oxide is present in a percentage by weight included between 0.050 and 0.20.

Finally, in the components referred to as "others" it is provided to be included all impurities present in the 10 starting materials and not of particular importance for the composition of the invention, from a technical point of view.

Within the general idea of the embodiment being the 15 object of claim 1, particularly advantageous are the component ranges referred to in claim 5 surprisingly ensuring an excellent compromise between bio-solubility, structural features, workability and costs. In addition, advantageously, even if bio-solubility was facilitated 20 and improved due to relatively high concentrations by weight of the alkaline oxides, the fiber brittleness effects caused by the latter are mitigated through an increase in B_2O_3 to such an extent that the fiber-forming features and production costs are not impaired.

25 More specifically, in accordance with the concrete form disclosed in claim 6 a good biological degradability was obtained and an increase in the combination ($\text{B}_2\text{O}_3 + \text{P}_2\text{O}_5$) was conceived in order to compensate for a reduction in 30 the amount by weight of Al_2O_3 and for an increase in the alkaline oxides that have reduced the structural resistance and increased the glass brittleness, respectively. In particular, the P_2O_5 action consists in efficiently increasing the structural features and bio- 35 solubility and the B_2O_3 component acts on the fiber elasticity, improves bio-solubility and does not reduce

the capability of the glass to be formed into fibers too much.

Still more specifically, in accordance with the concrete
5 form disclosed in claim 7, it is also simultaneously
solved the problem of protecting the apparatuses intended
for producing the fiber because the relatively high
concentrations of P_2O_5 involved (> 0.1 per cent by weight)
increase the biological degradability but are dangerous,
10 since P_2O_5 is an acid-hydrolysis hygroscopic oxide. In
addition, P_2O_5 is rather expensive. A preferred embodiment
of the composition of claim 7 is set out in claim 8,
according to the ranges therein stated.

15 The composition reproduced in claim 9 represents a valid
compromise between reducing the amount by weight of boron
oxide in order to reduce the glass fiber costs, and
limiting the damages caused to the furnaces due to a
relatively high presence of phosphoric oxide. The
20 embodiment of claim 10 represents a preferred form in
accordance with claim 9.

Finally, a composition having a high concentration by
weight of alumina in accordance with claim 13
25 surprisingly appears to be bio-soluble since magnesium
oxide helps in increasing solubility and also ensures a
better behaviour than calcium oxide when the fiber-
forming operations are carried out. In an original
manner, in the composition in accordance with claim 13,
30 with an alumina increase there is not a corresponding
variation in the calcium oxide content but an important
increase in magnesium oxide and boron oxide content since
one improves bio-sensitivity and the fiber-forming
operations and the other improves elasticity and bio-
35 solubility.

Some particular embodiments of glass fiber compositions are given hereinafter by way of non-limiting examples.

EXAMPLE NO. 1

5

A first illustrative glass fiber composition in accordance with the invention has the following components the concentration of which is expressed in percent by weight:

10	- SiO ₂ :	63.95;
	- Al ₂ O ₃ :	1.10;
	- CaO:	7.50;
	- MgO:	2.50;
	- Na ₂ O:	17.80;
15	- K ₂ O:	0.70;
	- B ₂ O ₃ :	6.00;
	- SO ₃ :	0.35;
	- Fe ₂ O ₃ :	0.10;
	- Others:	less than 2.

20

This glass was worked by centrifugal techniques. The water-solubility value was equal to 26 mg/g.

25 This evaluation of the resistance to water was carried out with the DGG (Deutsch Glassfasern Gesellschaft) method as also set out in the European Patent No. EP 738693A2.

30 According to this methodology, 10 g of glass, finely ground to 360-400 microns, is put in 100 ml of distilled water to the boiling point for 5 hours with a dropping cooler. After a quick cooling, the obtained solution is filtered, brought to volume and an aliquot is evaporated in a stove to 150°C, until complete dryness. The weight
35 of the dry residue enables the amount of glass dissolved in water to be known. As above indicated, the expression

of the results is in mg per gram of tested glass. As can be seen the glass in Example 1 has a water-solubility value which is not much higher than 200 mg/g, and this is a typical value of standard glasses.

5

The bio-degradability evaluated by bio-persistence tests in conformity with Protocol ECB/TM/26 rev. 7, 1998 gave rise, for fibers longer than 20 μ , to a weighted mean life of the fiber considerably lower than the 10 days required by the EEC directives 97/69/CE of 05.12.1997.

10

EXAMPLE NO. 2

A second glass fiber composition in accordance with the invention has the following components the concentrations of which are expressed in percent by weight:

15

- SiO₂: 64.95;
- Al₂O₃: 1.20;
- CaO: 7.00;
- 20 - MgO: 2.50;
- Na₂O: 17.80;
- K₂O: 0.70;
- B₂O₃: 4.40;
- P₂O₅: 1.00;
- 25 - SO₃: 0.35;
- Fe₂O₃: 0.10;
- Others: less than 2.

This glass was worked by centrifugal techniques. The value of the resistance to humidity detected by the DGG method is 32 mg/g. The bio-degradability evaluated by bio-persistence tests in conformity with Protocol ECB/TM/26 rev. 7, 1998 gave rise, for fibers longer than 20 μ , to a weighted mean life of the fiber considerably lower than the 10 days required by the EEC directives 97/69/CE of 05.12.1997.

30
35

EXAMPLE NO. 3

A third illustrative glass fiber composition in accordance with the invention has the following 5 components the concentrations of which are expressed in percent by weight:

	- SiO ₂ :	63.40;
	- Al ₂ O ₃ :	1,70;
	- CaO:	6.80;
10	- MgO:	3.60;
	- Na ₂ O:	17.60;
	- K ₂ O:	0.90;
	- B ₂ O ₃ :	5.90;
	- Fe ₂ O ₃ :	0.10;
15	- Others:	less than 2.

This glass was worked by centrifugal techniques. The value of resistance to humidity detected by the DGG method is 24 mg/g. The bio-degradability evalutated by 20 bio-persistence tests in conformity with Protocol ECB/TM/26 rev. 7, 1998 gave rise, for fibers longer than 20 μ , to a weighted mean life of the fiber considerably lower than the 10 days required by the EEC directives 97/69/CE of 05.12.1997.

25

For completion of the above descriptions, with reference to the compositions referred to in Example 1 and Example 2, the summarizing diagrams relating to the fibers of Example 1 and Example 2 showing the bio-persistence 30 features of the mentioned compositions are reproduced hereinafter.

These bio-persistence features were evalutated, as said, by analysing the capability of these fibers to be 35 evacuated from the inside of the pulmonary tissue of mice submitted to appropriate tests in conformity with the


provisions of document EU ECB/TM/26 Rev. 7, 1998.

Based on the foregoing, the bio-persistence features of the fibers were determined by calculating the index of T
5 1/2 mathematically describing the capability of the glass fibers to be evacuated from the pulmonary tissue of mice submitted to an experimental treatment.


As provided by the directives, the value of T 1/2 (lung
10 clearance half time) relates to fibers of a length greater than 20 μ .

Composition of Example 1

15



Composition of Example 2



C L A I M S

1. A biologically-degradable or bio-soluble glass fiber composition, characterized in that it comprises the following components expressed in percent by weight:

- SiO_2 : 61 to 66;
- Al_2O_3 : 1.1 to 2.1;
- $(\text{CaO}+\text{MgO})$: higher than 9;
- $(\text{Na}_2\text{O}+\text{K}_2\text{O})$: higher than 18;
- 10 - B_2O_3 : 4 to 15;
- P_2O_5 : 0 to 5;
- SO_3 : 0 to 1;
- Fe_2O_3 : 0 to 0.5;
- Others: less than 2.

15

2. The composition as claimed in claim 1, characterized in that it comprises the following components expressed in percent by weight:

- SiO_2 : 61 to 66;
- 20 - Al_2O_3 : 1.1 to 2.1;
- CaO : 6 to 9;
- MgO : 0 to 5;
- $(\text{Na}_2\text{O}+\text{K}_2\text{O})$: higher than 18;
- B_2O_3 : 4 to 15;
- 25 - P_2O_5 : 0 to 5;
- SO_3 : 0 to 1;
- Fe_2O_3 : 0 to 0.5;
- Others: less than 2.

30 3. The composition as claimed in claim 1, characterized in that it comprises the following components expressed in percent by weight:

- SiO_2 : 61 to 66;
- Al_2O_3 : 1.1 to 2.1;
- 35 - $(\text{CaO}+\text{MgO})$: higher than 9;
- Na_2O : higher than 17.5, lower than or equal

- to 23;
- K_2O : 0.6 to 2;
 - B_2O_3 : 4 to 15;
 - P_2O_5 : 0 to 5;
 - 5 - SO_3 : 0 to 1;
 - Fe_2O_3 : 0 to 0.5;
 - Others: less than 2.

4. The composition as claimed in anyone of the preceding
10 claims, characterized in that it comprises the following
components expressed in percent by weight:

- SiO_2 : 61 to 66;
- Al_2O_3 : 1.1 to 2.1;
- CaO : 6 to 9;
- 15 - MgO : 0 to 5;
- Na_2O : higher than 17.5, lower than or equal
to 23;
- K_2O : 0.6 to 2;
- B_2O_3 : 4 to 15;
- 20 - P_2O_5 : 0 to 5;
- SO_3 : 0 to 1;
- Fe_2O_3 : 0 to 0.5;
- Others: less than 2.

25 5. The composition as claimed in claim 4, characterized
in that it comprises the following components expressed
in percent by weight:

- SiO_2 : 61 to 66;
- Al_2O_3 : 1.1 to 1.80;
- 30 - $(CaO+MgO)$: higher than 9;
- Na_2O : 17.50 to 18.50;
- K_2O : 0.6 to 1;
- B_2O_3 : 5 to 15;
- P_2O_5 : 0 to 5;
- 35 - SO_3 : 0 to 1;
- Fe_2O_3 : 0 to 0.5;

- Others: less than 2.

6. The composition as claimed in claim 5, characterized in that it comprises the following components expressed in percent by weight:

- SiO_2 : 61 to 66;
- Al_2O_3 : 1.1 to 1.25;
- $(\text{CaO}+\text{MgO})$: higher than 9;
- Na_2O : 17.50 to 18.50;
- 10 - K_2O : 0.6 to 1;
- $(\text{B}_2\text{O}_3+\text{P}_2\text{O}_5)$: higher than 5;
- SO_3 : 0 to 1;
- Fe_2O_3 : 0 to 0.5;
- Others: less than 2.

15

7. The composition as claimed in claim 6, characterized in that it comprises the following components expressed in percent by weight:

- SiO_2 : 61 to 66;
- 20 - Al_2O_3 : 1.1 to 1.25;
- $(\text{CaO}+\text{MgO})$: higher than 9;
- Na_2O : 17.50 to 18.50;
- K_2O : 0.6 to 1;
- B_2O_3 : higher than 5;
- 25 - P_2O_5 : 0 to less than 0.1;
- SO_3 : 0 to 1;
- Fe_2O_3 : 0 to 0.5;
- Others: less than 2.

30 8. The composition as claimed in claim 7, characterized in that it comprises the following components expressed in percent by weight:

- SiO_2 : 61 to 66;
- Al_2O_3 : 1.1 to 1.25;
- 35 - $(\text{CaO}+\text{MgO})$: higher than 9;
- Na_2O : 17.50 to 18.50;

- K_2O : 0.6 to 1;
- B_2O_3 : higher than 5.5;
- P_2O_5 : 0 to less than 0.1;
- SO_3 : 0 to 1;
- 5 - Fe_2O_3 : 0 to 0.5;
- Others: less than 2.

9. The composition as claimed in claim 6, characterized in that it comprises the following components expressed
10 in percent by weight:

- SiO_2 : 61 to 66;
- Al_2O_3 : 1.1 to 1.25;
- $(CaO+MgO)$: higher than 9;
- Na_2O : 17.50 to 18.50;
- 15 - K_2O : 0.6 to 1;
- B_2O_3 : less than 5;
- P_2O_5 : 0.75 to 1.5;
- SO_3 : 0 to 1;
- Fe_2O_3 : 0 to 0.5;
- 20 - Others: less than 2.

10. The composition as claimed in claim 9, characterized in that it comprises the following components expressed in percent by weight:

- 25 - SiO_2 : 61 to 66;
- Al_2O_3 : 1.1 to 1.25;
- $(CaO+MgO)$: higher than 9;
- Na_2O : 17.50 to 18.50;
- K_2O : 0.6 to 1;
- 30 - B_2O_3 : less than 4.5;
- P_2O_5 : 0.75 to 1.5;
- SO_3 : 0 to 1;
- Fe_2O_3 : 0 to 0.5;
- Others: less than 2.

35

11. The composition as claimed in claim 5, characterized

in that it comprises the following components expressed in percent by weight:

- SiO_2 : 61 to 66;
- Al_2O_3 : 1.1 to 1.25;
- 5 - $(\text{CaO}+\text{MgO})$: higher than 9;
- Na_2O : 17.50 to 18.50;
- K_2O : 0.6 to 1;
- B_2O_3 : 5 to 15;
- P_2O_5 : 0 to 5;
- 10 - SO_3 : 0.1 to 0.5;
- Fe_2O_3 : 0 to 0.5;
- Others: less than 2.

12. The composition as claimed in claim 5, characterized in that it comprises the following components expressed in percent by weight:

- SiO_2 : 61 to 66;
- Al_2O_3 : 1.1 to 1.25;
- $(\text{CaO}+\text{MgO})$: higher than 9;
- 20 - Na_2O : 17.50 to 18.50;
- K_2O : 0.6 to 1;
- B_2O_3 : 5 to 15;
- P_2O_5 : 0 to 5;
- SO_3 : 0 to 1;
- 25 - Fe_2O_3 : 0.05 to 0.2;
- Others: less than 2.

13. The composition as claimed in claim 5, characterized in that it comprises the following components expressed in percent by weight:

- SiO_2 : 61 to 66;
- Al_2O_3 : 1.6 to 1.8;
- $(\text{CaO}+\text{MgO})$: higher than 9;
- MgO : higher than 3;
- 35 - MgO : preferably higher than 3.50;
- Na_2O : 17.50 to 18.50;

- K_2O : 0.6 to 1.5;
- B_2O_3 : 5 to 15;
- P_2O_5 : less than 0.1;
- SO_3 : less than 0.35;
- 5 - Fe_2O_3 : higher than zero;
- Others: less than 2.

14. The composition as claimed in claim 5, characterized
in that it comprises the following components expressed
10 in percent by weight:

- SiO_2 : 61 to 66;
- Al_2O_3 : 1.6 to 1.8;
- $(CaO+MgO)$: higher than 9;
- (Na_2O+K_2O) : higher than or equal to 18.5 and
15 lower than or equal to 23;
- K_2O : 0.6 to 1.5;
- B_2O_3 : 5 to 15;
- P_2O_5 : less than 0.1;
- SO_3 : 0.1 to 0.25;
- 20 - Fe_2O_3 : higher than 0;
- Others: less than 2.

15. The composition as claimed in claim 5, characterized
in that it comprises the following components expressed
25 in percent by weight:

- SiO_2 : 61 to 66;
- Al_2O_3 : 1.6 to 1.8;
- $(CaO+MgO)$: higher than 9;
- MgO : higher than 3;
- 30 - MgO : preferably higher than 3.50;
- (Na_2O+K_2O) : higher than or equal to 18.5 and
lower than or equal to 23;
- K_2O : 0.6 to 1.5;
- B_2O_3 : 5 to 15;
- 35 - P_2O_5 : less than 0.1;
- SO_3 : 0.1 to 0.25;

- Fe_2O_3 : higher than 0;
- Others: less than 2.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IT 00/00380

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C03C13/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
E	EP 1 048 625 A (POLIGLAS SA) 2 November 2000 (2000-11-02) claims; examples C1,C6; table 1	1,2
A	WO 98 43923 A (JOHNS MANVILLE INT INC) 8 October 1998 (1998-10-08) claims; examples	1-15
A	EP 0 588 251 A (SCHULLER INT INC) 23 March 1994 (1994-03-23) claims; examples	1-15
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the International filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the International filing date but later than the priority date claimed

- "T" later document published after the International filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

22 January 2001

Date of mailing of the international search report

29/01/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Van Bommel, L

INTERNATIONAL SEARCH REPORT

International Application No
PCT/IT 00/00380

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	POTTER R M ET AL: "GLASS FIBER DISSOLUTION IN A PHYSIOLOGICAL SALINE SOLUTION" GLASTECHNISCHE BERICHTE, DE, VERLAG DER DEUTSCHEN GLASTECHNISCHEN GESELLSCHAFT. FRANKFURT, vol. 64, no. 1, 1991, pages 16-28, XP000178832 table 2	1-15
P, A	FR 2 781 788 A (SAINT GOBAIN ISOVER) 4 February 2000 (2000-02-04) claims; examples	1-15

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IT 00/00380

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1048625	A	02-11-2000	NONE	
WO 9843923	A	08-10-1998	US 5945360 A	31-08-1999
			AU 6768898 A	22-10-1998
			CA 2255626 A	08-10-1998
			EP 0915812 A	19-05-1999
			JP 2000511508 T	05-09-2000
EP 0588251	A	23-03-1994	US 5401693 A	28-03-1995
			AT 151061 T	15-04-1997
			CA 2106412 A, C	19-03-1994
			DE 69309374 D	07-05-1997
			DE 69309374 T	23-10-1997
			DK 588251 T	29-09-1997
			EP 0739862 A	30-10-1996
			JP 2588360 B	05-03-1997
			JP 6321578 A	22-11-1994
			US 5981414 A	09-11-1999
FR 2781788	A	04-02-2000	NONE	